

Attributes & Properties^{\log}

Name:	351H INTREPID® Filtration Media
Color:	White
Basis Weight:	 2.0 ounces per square yard Range 1.90 to 2.10 ounces per square yard (67.8 grams / square meter) Range 64.4 to 71.2 grams per square meter
Efficiency:	42.0 % Minimum 38% TSI Model 8130 automated filter tester with 0.1 μm count median diameter NaCl particles at 85 liters per minute.
Air Permeability:	 490 cubic feet of air/minute per square foot of media Range 435 to 545 cfm (2.49 cubic meter of air / second per square meter of media) Range 2.21 to 2.77 meter³ / sec per meter² of media Textest FX 3300 Labotester III
Thickness:	0.064 inches (1.6 millimeters) Testing load of 0.025 psi (172.4 Pascals)
Inside Core Diameter:	6.75 inches (171 millimeter)
Roll Length:	1,500 linear yards (1,372 linear meters)
Roll Diameter:	45 inches (1143 millimeters) estimated
Slit Width Tolerance:	+1/4, -1/8 inch Slit width tolerance measured at the outside of the roll, under tension.
Air Entering Side:	The air entering side of the filter media faces the core.

⁶ Unless otherwise noted, the material described in this document is available for commercial sale and sold with a limited warranty. Kimberly-Clark Corporation and/or Kimberly-Clark Worldwide retains all intellectual property rights to this material, including trademarks and trade names. If the material described is defined as developmental, the material properties are estimates only and are not warranted by Kimberly-Clark Corporation.



Attributes & Properties^{\log}

Name:	351H INTREPID® Filtration Media	page 2 of 2	
Packaging:	Cardboard headers, full stretch wrap coverage, multiple slit rolls of the same width may be packaged together into a Powerpack		
Roll Labeling Informa	tion:		
	Slit Roll Label Slit roll number Product name and description Production date Basis weight Slit width Roll length Roll weight Country of origin		
	Powerpack Label Powerpack number Product name and description Production date Basis weight Roll weight Slit width Total square yards in the powerpack Total linear yards in the powerpack Country of origin		
oduction Reference:	NWFP-00139/2		

Revision: NJZ 06/02/2010

⁶ Unless otherwise noted, the material described in this document is available for commercial sale and sold with a limited warranty. Kimberly-Clark Corporation and/or Kimberly-Clark Worldwide retains all intellectual property rights to this material, including trademarks and trade names. If the material described is defined as developmental, the material properties are estimates only and are not warranted by Kimberly-Clark Corporation.